

**Einsatzbeispiele /  
Applications**

Fertigverpreßbare Masse zur uniaxialen und isostatischen Verarbeitung; für die Herstellung von oxidkeramischen Erzeugnissen, wie z.B. Mahlmedien, Isolatoren und verschleißfeste Teile.

Feedstock ready to press for uniaxial and isostatic pressing for the production of oxide ceramic bodies such as grinding media, insulating and wear-resistant parts, etc.

**Durchschnittswerte /  
Typical values**

Al <sub>2</sub> O <sub>3</sub>	[%]	≈ 98
CaO		≈ 0.6
Na <sub>2</sub> O		≤ 0.1
SiO <sub>2</sub>		≈ 1.0
Fe <sub>2</sub> O <sub>3</sub>		≤ 0.1
MgO		≈ 0.4
<hr/>		
Glühverlust / Loss on Ignition	[%]	≈ 3
<hr/>		
Schüttdichte / Bulk Density	[kg/m <sup>3</sup> ]	≈ 1200
<hr/>		
Feuchte / Moisture	[%]	≤ 0.35
<hr/>		
mittlerer Granulatdurchmesser / median granule size (Siebung / Screening)	[µm]	≈ 130
<hr/>		
Typische Verarbeitungseigenschaften/ Typical Processing Features:		
Pressdichte / Green Density	(100MPa) [g/cm <sup>3</sup> ]	≈ 2.45
Sinterdichte / Fired Density	(1600°C, 2h) [g/cm <sup>3</sup> ]	≈ 3.88



## Shipping Information

Transportation classification: not regulated for transportation  
Harmonized tariff number: 28182000

Packaging and minimum order quantity information is available from sales or customer service.

## Safety and Handling Information

For specific safety, toxicity and handling information, please refer to the material safety data sheet on this product.

## Chemical Registration Numbers

Chem. Bezeichnung: Aluminiumoxid  
Formel:  $Al_2O_3$   
CAS No. : 1344-28-1  
EG-/EINECS No.: 215-691-6  
UN-Nr.: ~



ALBEMARLE and the Albemarle signet are registered trademarks of Albemarle Corporation.

The information presented herein is believed to be accurate and reliable, but is presented without guarantee or responsibility on the part of Albemarle Corporation. It is the responsibility of the user to comply with all applicable laws and regulations and to provide for a safe workplace. The user should consider any information contained herein, including information about any health or safety hazards, only as a guide, and should take those precautions that are necessary or prudent to instruct employees and to develop work practice procedures in order to promote a safe work environment. Further, nothing contained herein shall be taken as an inducement or recommendation to manufacture or use any of the herein described materials or processes in violation of existing or future patents.

Issue: October 2007  
© 2007 Albemarle Corporation

### AMERICAS

Albemarle Corporation  
451 Florida Street  
Baton Rouge, Louisiana 70801  
Phone: +1-225-388-7402  
Fax: +1-225-388-7848

### EUROPE, MIDDLE EAST, AFRICA

Albemarle Europe SPRL  
Parc Scientifique de LLN  
Rue du Bosquet 9  
B-1348 Louvain-la-Neuve Sud, Belgium  
Phone: +32-10-48-1711  
Fax: +32-10-48-1717

Martinswerk GmbH  
Kölner Straße 110  
D-50127 Bergheim  
Phone: +49-2271-902-465  
Fax: +49-2271-902-710

### ASIA PACIFIC

Albemarle Asia Pacific Company  
480 Lorong 6 Toa Payoh  
#16-01 HDB Hub East Wing  
Singapore 310480  
Phone: +65-6424-8400  
Fax: +65-6424-8401

Albemarle Overseas Development Corporation  
16th Floor, Fukoku Seimei Building  
2-2, Uchisaiwaicho, 2-Chome  
Chiyoda-ku, Tokyo 100-0011, Japan  
Phone: +81-3-5251-2541  
Fax: +81-3-3500-2547

Albemarle Chemicals China Corporation  
Room 2208, Shui On Plaza  
No. 333 Huaihai Zhong Road,  
Shanghai 200021, China  
Phone: +86-21-5306-1360  
Fax: +86-21-5306-2420

Albemarle China Corporation  
China World Tower, Room 1317  
No. 1 Jian Guo Men Wai Avenue  
Beijing 100004, China  
Phone: +86-10-6505-4153 and -54  
Fax: +86-10-6505-4150

Albemarle Korea Corporation  
602 Trade Tower  
World Trade Center  
159-1 Samsung-dong, Kangnam-gu,  
135-729 Seoul, Korea  
Phone: +82-2-555-3005  
Fax: +82-2-555-3002

### INTERNET

www.albemarle.com  
www.martinswerk.de