

Einsatzbeispiele /
Applications

MAGNIFIN H-7 C3 ist ein hochreines Magnesiumhydroxid, das mit einer speziellen Fettsäure beschichtet wurde. Die mineralische Rohstoffbasis sowie ein patentierter Prozess garantieren einen gleichmäßigen Kristallaufbau.

MAGNIFIN H-7 C3 wird empfohlen für die halogenfreie, flammwidrige und rauchunterdrückende Ausrüstung von Kunststoffen und Elastomeren, z.B. EVA, EPDM und PVC. Die Wirkung basiert auf einer thermischen Zersetzung, die erst bei ca. 340°C beginnt. Dabei entstehen keine toxischen und korrosiven Gase. Die Oberflächenbehandlung unterstützt die Verträglichkeit des Füllstoffes mit der Polymermatrix und verbessert somit die mechanischen Eigenschaften des Compounds.

MAGNIFIN H-7 C3 is a high-purity magnesium hydroxide, treated with a special fatty acid coating. Based on a mineral raw material, the patented process guarantees a regular structure of the crystallite.

MAGNIFIN H-7 C3 is tailor-made for plastic and elastomer applications, e.g. EVA, EPDM and PVC, and represents a halogen free flame retardant with low smoke emission and high thermal stability up to 340°C. During the decomposition process no toxic and corrosive gases are generated. The surface treatment favours the compatibility of filler and polymer matrix and therefore improves the mechanical properties of the compound.

Spezifikation /
Specification

| | | | |
|---|--|-------------------------------------|--|
| Mg(OH) ₂ | [%] | ≥ 99.8 | (*) |
| Feuchte / Moisture (105°C) | [%] | ≤ 0.3 | (bei Absackung / when packed) |
| Spezifische Oberfläche / Specific Surface Area (BET) | [m ² /g] | 5.0 – 8.0 | |
| Elektrische Leitfähigkeit / Electrical Conductivity | [μS/cm] | ≤ 200 | (10 % Susp. in deion. Wasser / 10 % susp. in de-ion water) |
| Teilchengröße / Particle Size | d ₁₀ [μm] d ₅₀ [μm] d ₉₀ [μm] | 0.4 – 0.7 0.9 – 1.3 1.4 – 2.0 | } gemessen mit MALVERN MASTERSIZER 2000 (Laserbeugung) measured by MALVERN MASTERSIZER 2000 (laser diffraction) |
| Siebrückstand > 45 μm / Sieve Residue > 45 μm [%] | | ≤ 0.1 | |
| Schüttdichte / Bulk Density | [g/l] | 300 – 500 | |



Typische Werte / Typical Data

| | | | |
|--|----------------------|-------------|---|
| Glühverlust / Loss on Ignition 1200°C | [%] | 31 | (*) |
| Dichte / Density | [g/cm ³] | 2.4 | (*) |
| Mohssche Härte / Mohs Hardness | | 2.5 | (*) |
| Brechungsindex / Refraction Index | | 1.56 – 1.58 | (*) |
| Weißgrad / Whiteness (DR LANGE 457 nm) | [%] | > 96 | (*) |
| Al ₂ O ₃ | [ppm] | < 50 | } Bestimmung mittels XRF an MAGNIFIN H-7 measured by XRF on MAGNIFIN H-7 |
| Fe ₂ O ₃ | [ppm] | < 50 | |
| MnO | [ppm] | < 10 | |
| CaO | [ppm] | < 50 | |
| SiO ₂ | [ppm] | < 200 | |
| NiO | [ppm] | < 50 | |
| Cr ₂ O ₃ | [ppm] | < 10 | |
| B ₂ O ₃ | [ppm] | < 1 | |
| Cu | [ppm] | < 10 | |

(*) Werte mit einem Sternchen versehen beziehen sich auf das unbeschichtete Substrat.
(*) Values with an asterisk refer to the uncoated substrate.

Die oben genannten Werte sind nur als Richtwerte zu verstehen und nicht etwa als zugesicherte Eigenschaften.
The above mentioned values should be taken only as indications and not as guaranteed properties.

Shipping Information

Transportation classification: not regulated for transportation
Harmonized tariff number: 28161000

Packaging and minimum order quantity information is available from sales or customer service.

Safety and Handling Information

For specific safety, toxicity and handling information, please refer to the material safety data sheet on this product.

Chemical Registration Numbers

Chem. Bezeichnung / Chem. name: Magnesium hydroxide
Formel / formula: Mg(OH)₂
CAS No.: 130942-8
EC/EINECS No.: 215-170-3

ALBEMARLE®

ALBEMARLE and the Albemarle signet are registered trademarks of Albemarle Corporation.

The information presented herein is believed to be accurate and reliable, but is presented without guarantee or responsibility on the part of Albemarle Corporation. It is the responsibility of the user to comply with all applicable laws and regulations and to provide for a safe workplace. The user should consider any information contained herein, including information about any health or safety hazards, only as a guide, and should take those precautions that are necessary or prudent to instruct employees and to develop work practice procedures in order to promote a safe work environment. Further, nothing contained herein shall be taken as an inducement or recommendation to manufacture or use any of the herein described materials or processes in violation of existing or future patents.

Issue: January 2011
© 2011 Albemarle Corporation

AMERICAS
Albemarle Corporation
451 Florida Street
Baton Rouge, Louisiana 70801
Phone: +1-225-388-7402
Fax: +1-225-388-7848

**EUROPE, MIDDLE EAST,
AFRICA**
Albemarle Europe SPRL
Parc Scientifique de LLN
Rue du Bosquet 9
B-1348 Louvain-la-Neuve Sud, Belgium
Phone: +32-10-48-1711
Fax: +32-10-48-1717

Martinswerk GmbH
Kölner Straße 110
D-50127 Bergheim
Phone: +49-2271-902-465
Fax: +49-2271-902-710

ASIA PACIFIC
Albemarle Asia Pacific Company
480 Lorong 6 Toa Payoh
#16-01 HDB Hub East Wing
Singapore 310490
Phone: +65-6424-8400
Fax: +65-6424-8401

**Albemarle Overseas Development
Corporation**
16th Floor, Fukoku Seimei Building
2-2, Uchisaiwaicho, 2-Chome
Chiyoda-ku, Tokyo 100-0011, Japan
Phone: +81-3-5251-0796
Fax: +81-3-3500-2547

**Albemarle Chemicals China
Corporation**
Room 2208, Shui On Plaza
No. 333 Huaihai Zhong Road,
Shanghai 200021, China
Phone: +86-21-6103-8666
Fax: +86-21-6103-8777

Albemarle China Corporation
China World Tower, Room 1317
No. 1 Jian Guo Men Wai Avenue
Beijing 100004, China
Phone: +86-10-6505-4153 and -54
Fax: +86-10-6505-4150

Albemarle Korea Corporation
602 Trade Tower
World Trade Center
159-1 Samsung-dong, Kangnam-gu,
135-729 Seoul, Korea
Phone: +82-2-555-3005
Fax: +82-2-555-3002

INTERNET
www.albemarle.com
www.martinswerk.de